

## Certificate of Analysis CRM 108-A Monazite Sand – Silica Mixture Thorium Standard

Thorium:  $0.0515_5 \pm 0.0002_3 \text{ Wt.\%}$ 

 $(\alpha = 0.05, df = 9)$ 

\*Uranium (calculated): 0.00205 Wt.%

This Certified Reference Material (CRM) was prepared by milling and blending NBL CRM 7-A Monazite Sand (9.7% ThO<sub>2</sub>) with silica (99.9% SiO<sub>2</sub>) to obtain a uniform mixture of desired thorium concentration. Characterization and certification analyses for uranium content were performed on ten (10) units selected from the packaged final product.

The certified value listed above is expressed in terms of 95% confidence limits, defined as as  $\overline{x} \pm \sigma^- t$ , where  $\overline{x}$  is the unweighted mean of the measurement data,  $\sigma$  is the standard deviation of the mean, and t is the Student's t value for the indicated degrees of freedom (df) and at the 5% significance level ( $\alpha$ ).

REFERENCE METHODS OF ANALYSIS: Spectrophotometry verified with NBL Thorium Oxide (ThO<sub>2</sub>).

\*Calculation is based on the uranium oxide  $(U_3O_8)$  value of  $0.399_3 \pm 0.017_1$  Wt%  $U_3O_8$  for NBL CRM 7-A Monazite Sand.

March 1, 2008 Argonne, Illinois

www.nbl.doe.gov Page 1 of 1 Jon Neuhoff, Director New Brunswick Laboratory